

# Problem Solving

## Removal of Enrich 'N' Seal or Stone Enhancer Residue

**PROTECTING YOUR INVESTMENT:** The timeless beauty and inherent durability of natural stone makes it a favorite surfacing material for designers, architects and homeowners. Because of geological composition, certain stones may require different care and maintenance techniques. To remove Aqua Mix Enrich 'N' Seal or Stone Enhancer, the following guidelines are recommended:

**Method A:** For removal of Aqua Mix Enrich 'N' Seal or Stone Enhancer residue within 48 hours of application.

**Product Recommendation:** Aqua Mix Heavy Duty Tile & Grout Cleaner or Stone Deep Clean.

**Equipment:** Nylon scrub brush, mop and bucket with wringer or wet/dry vacuum.

**Optional:** For large installations a low RPM (150-350 RPM) floor machine may be used fitted with a soft to medium bristle brush or hogs hair pad.

**Coverage:** Approximately 150 - 300 sq. ft. (14 m<sup>2</sup> – 28 m<sup>2</sup>) per gallon (3.785 L) of diluted product.

**Procedure:**

- » Always test a small area first.
- » Mix one part Heavy-Duty Tile & Grout Cleaner or Stone Deep Clean to two parts water.
- » Apply solution onto surface and allow to dwell for 5 to 10 minutes.
- » Agitate by hand with scrub brush or with floor machine. Keep surface wet throughout process.
- » Remove solution with mop or wet/dry vacuum.
- » Rinse several times with clean water and allow to dry.

**Method B:** For removal of Aqua Mix Enrich 'N' Seal or Stone Enhancer residue after 48 hours of application.

**Product Recommendation:** Aqua Mix Sealer & Coating Remover.

**Equipment:** Nylon or natural-bristle scrub brush, mop and bucket with wringer or wet/dry vacuum.

**Optional:** For large installations a low RPM (150-350 RPM) floor machine may be used fitted with a soft to medium bristle brush or hogs hair pad.

**Coverage:** Approximately 75 - 200 sq. ft. (7 m<sup>2</sup> – 19 m<sup>2</sup>) per gallon (3.785 L).

**Procedure:**

- » Always test a small area first.
- » Apply a liberal amount of Sealer & Coating Remover to a small, manageable area of up to 25 sq. ft. (2 m<sup>2</sup>)
- » Allow to dwell for up to 2 hours for residue to soften.
- » Agitate by hand with scrub brush or with floor machine.
- » If necessary, apply small amounts of additional remover or apply more water.
- » Remove solution with mop or wet/dry vacuum.
- » Rinse several times with clean water and allow to dry.

**Considerations:** Do not use Aqua Mix Sealer & Coating Remover on synthetic agglomerate or other resinous surfaces.

This recommendation is intended as a guideline for the removal of Enrich 'N' Seal or Stone Enhancer residue. The actual cleaning requirements may vary depending on type of tile, method of application, texture of stone and amount of residue. **READ PRODUCT DIRECTIONS THOROUGHLY PRIOR TO USE.**

**Aqua Mix Technical Assistance:**

- » Call 877.278.2311 Monday - Friday, 6:00 am to 4:30 pm or Saturday 7:00, am to 12:00 pm Pacific time.
- » Visit website at [www.aquamix.com](http://www.aquamix.com)
- » E-mail technical questions to [tech@aquamix.net](mailto:tech@aquamix.net)